

PRODUCT SPECIFICATION SHEET

BELZONA 1511

FN10178



GENERAL INFORMATION

Product Description:

A two component high temperature paste grade system for rebuilding metals damaged by erosion-corrosion. When cured, the material is durable yet fully machinable. The product has been specifically designed for use with Belzona High Temperature coatings. Also used as a high strength structural adhesive for bonding or for creation of irregular load bearing shims with good electrical insulation characteristics. For use in Original Equipment Manufacture or repair situations.

Application Areas:

Rebuilding erosion-corrosion and/or smoothing welds, etc., prior to application of Belzona High Temperature coatings.

APPLICATION INFORMATION

Working Life

Will vary according to temperature. At 68°F (20°C) the usable life of mixed material is 60 minutes.

Application Methods

Spatula/Applicator

Application Temperature

Application should occur in the following ambient temperature range: 50°F/10°C to 104°F/40°C

Cure Time

Cure times before returning to service will vary depending on the ambient conditions and whether overcoated with a Belzona coating. Consult the Belzona IFU for specific details.

Overcoat Time

The maximum overcoat time is 24 hours.

Volume Capacity

23.4in³ (383cm³)/kg.

Base Component

Appearance	Paste
Color	Dark gray
Gel strength at 77°F (25°C)	>120 g/cm QH
Density	2.88 - 2.92 g/cm ³

Solidifier Component

Appearance	Paste
Color	Light gray
Gel strength at 77°F (25°C)	>30 g/cm QV
Density	1.72 - 1.76 g/cm ³

Mixed Properties

Mixing Ratio by Weight (Base : Solidifier)	5 : 1
Mixed Form	Paste
Slump Resistance	nil at 0.5 inch (1.27 cm)
Mixed Density	2.61 g/cm ³
VOC content (ASTM D2369 / EPA ref. 24):	0.06% / 1.66g/L

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 1511

FN10178



ABRASION

Taber

Dry sliding abrasion resistance, when determined in accordance with ASTM D4060 using CS17 wheels, will typically result in:

12.8 mm³ loss per 1000 cycles
(212°F/100°C cure & 68°F/20°C test)

Wet sliding abrasion resistance, when determined in accordance with ASTM D4060 using H10 wheels, will typically result in:

591 mm³ loss per 1000 cycles
(212°F/100°C cure & 68°F/20°C test)

ADHESION

Cleavage Adhesion

The Cleavage Strength when applied to grit blasted mild steel, as determined in accordance with ASTM D1062, will typically be:

1770 pli / 315 N/mm (68°F/20°C cure & test)
 1570 pli / 235 N/mm (212°F/100°C cure & 68°F/20°C test)
 1490 pli / 215 N/mm (320°F/160°C cure & 68°F/20°C test)
 1360 pli / 194 N/mm (212°F/100°C cure & test)
 840 pli / 103 N/mm (320°F/160°C cure & test)

Pull Off Adhesion

The PosiTest Dolly Pull Off Strength on 10mm thick grit blasted mild steel, as determined in accordance with ASTM D4541 and ISO 4624, will typically be:

5180 psi / 35.7 MPa (68°F/20°C cure)
 5160 psi / 35.6 MPa (212°F/100°C cure)
 4700 psi / 32.4 MPa (320°F/160°C cure)

Tensile Shear Adhesion

The Tensile Shear Adhesion on grit blasted mild steel, as determined in accordance with ASTM D1002, will typically be:

3060 psi / 21.1 MPa (68°F/20°C cure & test)
 2780 psi / 19.2 MPa (212°F/100°C cure & 68°F/20°C test)
 2980 psi / 20.5 MPa (320°F/160°C cure & 68°F/20°C test)
 2400 psi / 16.5 MPa (212°F/100°C cure & test)
 1700 psi / 11.7 MPa (320°F/160°C cure & test)

CHEMICAL ANALYSIS

The mixed **Belzona 1511** has been independently analyzed for halogens, heavy metals, and other corrosion-causing impurities, with the following typical results:

Analyte	Total Concentration (ppm)
Fluoride	333
Chloride	463
Bromide	ND (<23)
Sulfur	7363
Zinc	24.5
Tin	2.2
Antimony, Arsenic, Bismuth, Cadmium, Lead, Silver, Mercury, Gallium and Indium	ND (<2.0)

Analyte	Leachable Concentration (ppm)
Fluoride	2
Chloride	14
Bromide	ND (<6)
Sulfur (S ₁)	49
Sulfur (S ₂)	57
Nitrite	2
Nitrate	6

ND : Not Detected

COMPRESSIVE PROPERTIES

When determined in accordance with ASTM D695, typical values will be:

Maximum Compressive Strength

10,490 psi / 72.3 MPa (68°F/20°C cure & test)
 17,570 psi / 121.2 MPa (212°F/100°C cure & 68°F/20°C test)
 18,980 psi / 130.8 MPa (320°F/160°C cure & 68°F/20°C test)
 10,790 psi / 74.4 MPa (212°F/100°C cure & test)
 7,610 psi / 52.2 MPa (320°F/160°C cure & test)

Compressive Yield Strength

7690 psi / 53.0 MPa (68°F/20°C cure & test)
 10250 psi / 70.7 MPa (212°F/100°C cure & 68°F/20°C test)
 10590 psi / 73.0 MPa (320°F/160°C cure & 68°F/20°C test)
 6380 psi / 44.0 MPa (212°F/100°C cure & test)
 3040 psi / 20.9 MPa (320°F/160°C cure & test)

Compressive Modulus

1.69x10⁵ psi / 1170 MPa (68°F/20°C cure & test)
 1.61x10⁵ psi / 1110 MPa (212°F/100°C cure & 68°F/20°C test)
 1.58x10⁵ psi / 1090 MPa (320°F/160°C cure & 68°F/20°C test)
 1.29x10⁵ psi / 890 MPa (212°F/100°C cure & test)
 0.76x10⁵ psi / 520 MPa (320°F/160°C cure & test)

CORROSION PROTECTION

Salt Spray

When tested in accordance with ASTM B117, the coating will show no signs of failure after 1000 hours continuous exposure.

PRODUCT SPECIFICATION SHEET

BELZONA 1511

FN10178



ELONGATION & TENSILE PROPERTIES

When determined in accordance with ASTM D638, typical values will be:

Tensile Strength

4230 psi / 29.2 MPa	(68°F/20°C cure & test)
4670 psi / 32.2 MPa	(212°F/100°C cure & 68°F/20°C test)
3860 psi / 26.6 MPa	(320°F/160°C cure & 68°F/20°C test)
2550 psi / 17.6 MPa	(212°F/100°C cure & test)
2040 psi / 14.1 MPa	(320°F/160°C cure & test)

Elongation

0.51 %	(68°F/20°C cure & test)
0.55 %	(212°F/100°C cure & 68°F/20°C test)
0.54 %	(320°F/160°C cure & 68°F/20°C test)
0.52 %	(212°F/100°C cure & test)

Young's Modulus

9.44x10 ⁵ psi / 6510 MPa	(68°F/20°C cure & test)
7.98x10 ⁵ psi / 5500 MPa	(212°F/100°C cure & 68°F/20°C test)
7.31x10 ⁵ psi / 5040 MPa	(320°F/160°C cure & 68°F/20°C test)
5.73x10 ⁵ psi / 3950 MPa	(212°F/100°C cure & test)
1.53x10 ⁵ psi / 1050 MPa	(320°F/160°C cure & test)

FLEXURAL PROPERTIES

When determined in accordance with ASTM D790, typical values will be:

Flexural Strength

8840 psi / 61.0 MPa	(68°F/20°C cure & test)
9790 psi / 67.5 MPa	(212°F/100°C cure & 68°F/20°C test)
8760 psi / 60.4 MPa	(320°F/160°C cure & 68°F/20°C test)
7640 psi / 52.7 MPa	(212°F/100°C cure & test)
4310 psi / 29.7 MPa	(320°F/160°C cure & test)

Flexural Modulus

8.56x10 ⁵ psi / 5900 MPa	(68°F/20°C cure & test)
6.69x10 ⁵ psi / 4610 MPa	(212°F/100°C cure & 68°F/20°C test)
6.99x10 ⁵ psi / 4820 MPa	(320°F/160°C cure & 68°F/20°C test)
4.74x10 ⁵ psi / 3270 MPa	(212°F/100°C cure & test)
2.42x10 ⁵ psi / 1670 MPa	(320°F/160°C cure & test)

HARDNESS

The Shore D and Barcol hardness, when determined in accordance with ASTM D2240 and ASTM D2583, will typically be:

	68°F/20°C cure	212°F/100°C cure	320°F/160°C cure
Shore D	84	87	89
Barcol	80	83	85

HEAT RESISTANCE

Heat Distortion & Glass Transition Temperature (HDT & T_g)

The HDT and T_g when determined in accordance with ASTM D648 and ISO 11357-2 respectively, following a 7 day cure period, will typically be:

Cure temperature	HDT	T _g
68°F/20°C	127°F/53°C	129°F/54°C
212°F/100°C	268°F/131°C	277°F/136°C
284°F/140°C	333°F/167°C	-
320°F/160°C	356°F/180°C	356°F/180°C

Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO11357 is typically 410°F (210°C).

Atlas Cell Cold Wall Immersion Test

When tested in accordance with NACE TM0174 procedure A, **Belzona 1511** at a thickness up to 0.5 in. (12mm) and overcoated with **Belzona 1593** system, will result in no rusting (ASTM D610 rating 10) or blistering (ASTM D714 rating 10) after 6 months continuous immersion in water at 302°F/150°C.

IMPACT RESISTANCE

Izod Pendulum

Izod impact strength, when determined in accordance with ASTM D256, will typically be:

Reverse		
Notched:	3.5 KJ/m ²	(68°F/20°C cure & test)
	5.8 KJ/m ²	(212°F/100°C cure & 68°F/20°C test)
	3.9 KJ/m ²	(320°F/160°C cure & 68°F/20°C test)
Un-notched:	4.1 KJ/m ²	(68°F/20°C cure & test)
	6.6 KJ/m ²	(212°F/100°C cure & 68°F/20°C test)
	4.4 KJ/m ²	(320°F/160°C cure & 68°F/20°C test)

SHELF LIFE

Separate base and solidifier components shall have a shelf life of 5 years from date of manufacture when stored in their original unopened containers between 32°F (0°C) and 86°F (30°C).

PRODUCT SPECIFICATION SHEET

BELZONA 1511

FN10178



WARRANTY

This product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona ensures that all its products are carefully manufactured to ensure the highest quality possible and are tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 1511 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000 N.W. 88th Court,
Miami, Florida, USA, 33172

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2018 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

